

Serial No.: 10/675,224

MARKED COPY

COLORLESS GLASSES/BOROSILICATE
GLASSES WITH SPECIAL UV-EDGE

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to a borosilicate glass with a special absorption edge situation, and to uses for the borosilicate glass.

Discussion of Related Art

In order to filter, in a targeted manner, a UV range which generally is defined as below 400 nm and can be divided into three sub-ranges, UVA, UVB and UVC, so-called colorless glasses or also optical glasses with defined absorption edges ~~edge-situations~~ are used. The absorption edge situation or edge wavelength λ_c corresponds to half of the pure transmission maximum value between the blocking and permeable range.

A spectacle glass is known from European Patent Reference EP 0 151 346 B1 which has a UV edge in the range between 325 nm and 335 nm. TiO_2 is added to the glass for this purpose. The proportion of TiO_2 is thus 4 - 6 % by weight on an oxide basis.

This type of glass is not suitable for commercial application cases, in which a dimensional stability even at high glass transformation temperatures, for example $> 560^\circ\text{C}$, and/or a stable thermal expansion coefficient is required.

A stable expansion coefficient facilitates the incorporation or respectively exchange of the glasses in components.

~~One~~ Another important aspect for the glasses in such technical applications is ~~also~~ their transmission course ~~inclusive of~~ including the UV edge. A defined steep UV edge is required in the UV range corresponding to the application

purpose. For example, for illumination tables for burning-in phosphorus units into television screen units, UV radiation of > 320 nm is required. For experiments with plants in plant cultivation, hard UV radiation of > 280 nm is also definitely used. Weathering instruments for quality control change the UV ranges, and thus filters according to each requirement.

Japanese Patent Reference JP 77-066 52-66512 A describes UV filter glass with an absorption edge ~~situations~~ of approximately 370 nm made of a borosilicate glass which necessarily contains CeO_2 and otherwise in combination with TiO_2 . The CeO_2 significantly increases the material costs in the glass. In addition, CeO_2 has a negative effect on the solarization of the glass.

German Patent Reference DE 639 456 A1 describes a lamp glass, made of a glass with a relatively wide composition range, in which SiO_2 , B_2O_3 are components and Al_2O_3 , MgO , CaO , BaO , BeO , Na_2O and K_2O can be contained. The glass has no defined UV edge or optical situations.

United Kingdom Patent Reference GB 20 02 341 describes an optical fibre glass with a relatively wide composition range, in which SiO_2 , B_2O_3 are components and Al_2O_3 , MgO , CaO , BaO , SrO , Na_2O and K_2O can be contained. The glass has no defined UV edge, but rather glasses/fibres with refraction index gradients.

United States Patent 2,832,491 corresponds to a method patent, which is suitable for pre-loading of glass panes. The composition of the glass which is suitable for pre-loading contains in turn SiO_2 and B_2O_3 as components in a relatively wide range. Exact UV edges and optical situations cannot be set with this glass.

German Patent Reference DE 195 32 800 A1 comprises the use of glasses for disinfection. A high transmission in the UVB and UVC range with reduced transmission in the visible and IR range is ensured by these glasses. Consequently, glasses with high transmission in the pass range are not possible.

German Patent Reference DE 38 22 733 A1 describes solder glass made of a glass with a relatively wide composition range, in which SiO_2 , B_2O_3 are components and Al_2O_3 , MgO , CaO , BaO , SrO , ZnO , Li_2O , Na_2O and K_2O can be contained, containing at most 1% by weight ~~alkali~~ alkaline earth metal oxides. An ~~alkali~~ alkaline earth content of at least 1% by weight ensures a good chemical resistance, which permits the application of these filter glasses in a humid climate. The glass taught by German Patent Reference DE 38 22 733 A1 does not make it possible to set a defined UV absorption edge ~~situation~~.

European Patent Reference EP 0 505 061 A1 describes glass for protection covers for gallium arsenide solar cells with high UV absorption in the wavelength range of less than 320 nm. It contains SiO_2 , B_2O_3 , Na_2O , K_2O and CeO_2 as components. Al_2O_3 , TiO_2 , MgO , CaO , ZnO , SrO , BaO , PbO , Li_2O , As_2O_3 , Sb_2O_3 and F are optionally contained, ~~optionally~~. High UV transmissions are specifically avoided in the case of the described glasses.

European Patent Reference EP 0 953 549 A1 describes glass for glass plates and substrates, which are used in electronics. The physical properties, such as expansion coefficient, the lower strain point, the density and the oxygen atom density are essential here. However, the UV absorption edge ~~situation~~ or the optical properties are not relevant for these glasses.

SUMMARY OF THE INVENTION

It is one object of this invention to provide a UV permeable glass, the absorption edge ~~situation~~ of which can be set in a defined and simple manner in a range between 280 and 325 nm[[, the]]. ~~The glass is being~~ dimensionally stable at high operating temperatures and ~~having~~ has a relatively constant thermal expansion coefficient.

This object can be achieved by a glass according to features described in this specification and in the claims.

The borosilicate glass which is used fulfills the requirements in temperature and dimensional stability. The borosilicate glass can thereby be made available with a defined absorption edge ~~situation~~ between 280 and 325 nm, with high transmission in the pass range, high optical density in the stop range and specific refraction indices and Abbé numbers. This is possible merely by varying the content of TiO_2 in the glass system.

The continuous production with ~~edge-situations~~ cut-off wavelengths λ_c of 280 to 325 nm is essential for these glasses. This continuous production is ensured because of the uniform base glass. TiO_2 is used as doping for the desired steep absorption edge ~~situation~~, an addition not required in the case of very low ~~edge-situations~~ cut-off wavelengths of < 290 nm. This type of production saves costs and time, for example it avoids long remelting phases, in which no usable glass is produced.

All the glasses described here, apart from being used as colorless glass with specific absorption edges ~~edge-situations~~, are used also as optical glasses with defined refraction indices n_d and dispersion v_d . As a result, uses in the field of imaging optics, projection, telecommunications, optical communications technology and microlithography are possible.

A glass with the desired optical and physical properties comprises preferably a basic glass system of 60 to 70% by weight SiO_2 , 10 to 15% by weight B_2O_3 , 5 to 15% by weight Na_2O , 5 to 10% by weight K_2O , 0.1 to 1% by weight CaO , 0.5 to 3 BaO , and optionally 0.5 - 2.5% SrO , 0.1 - 1% MgO , 0 to 5% by weight Li_2O (preferably Li free), 0 to 2 TiO_2 , 0 to 0.5% by weight Sb_2O_3 and normal refining agents.

The glass according to this invention contains SiO_2 in the % by weight range between 60 to 75%, preferably 65 to 75% by weight, and functions as glass former. Higher contents would impair the meltability, ~~in the case of~~ and lower contents[[,]] would make the glass formation difficult. Lower SiO_2 proportions in the glass would also result in Abbé numbers which are too low.

B_2O_3 is a glass former exactly like SiO_2 and improves the meltability by reducing the viscosity. ~~In the~~ The glass according to this invention~~[[,]]~~ contains 5 to 15% by weight B_2O_3 , and preferably 10 to 13% by weight,~~are contained~~. Lower contents than 5% by weight B_2O_3 would impair the meltability of the glasses, whereas higher contents than 15% by weight B_2O_3 impair the chemical resistance of the glass.

The contained alkali oxides Na_2O (5 to 15% by weight, and preferably 6 to 12% by weight) and K_2O (5 to 10% by weight) can improve the meltability, for example to reduce the viscosity. With alkali contents which are too high, above all the hydrolytic resistance would be impaired, but also, to a lesser extent, the resistance to alkali liquor. Above all, however, the Abbé number is reduced too greatly.

Of the ~~alkali~~ alkaline earth oxides, CaO with 0.1 to 1% by weight, and preferably 0.1 to 0.5% by weight, and BaO with 0.5 to 3% by weight, preferably 0.5 to 2.5% by weight, are contained in the glass according to this invention. The ~~alkali~~ alkaline earth oxides reduce the melt viscosity, repress the crystallisation and contribute to improving the resistance to alkali. CaO is thus present in the glass at least with 0.1% by weight and BaO with at least 0.5% by weight. Both oxides are likewise indispensable for the setting of the optical situation. With higher contents, the Abbé number in turn may be reduced too greatly.

TiO_2 is ~~required~~ as an optional component for setting the UV situations greater than 280 nm. However more than 1.7% by weight of TiO_2 in the glass scarcely still effects a noticeable displacement of the UV edge in the longer-

wave range in this glass system, and promotes devitrification. In addition, too high an amount contents of TiO_2 , as indicated, ~~would increase~~ generally increases the refractive index too greatly and reduce the Abbé number too greatly.

The glass can be manufactured free of expensive CeO_2 apart from unavoidable impurities. This is advantageous for the steepness of the transmission curve during the transition from the stop to the pass range and for the solarisation resistance.

The glass can also be free of PbO and of As_2O_3 apart from unavoidable impurities. The glass can thus be free of toxic components and therefore can be ecologically harmless.

Sb_2O_3 is optionally a component and serves for use as refining agent. However, other normal refining agents are likewise possible.

BRIEF DESCRIPTION OF THE DRAWING

Fig. 1 shows a graphical representation of an absorption edge situation for a given glass composition.

DESCRIPTION OF PREFERRED EMBODIMENTS

Normal optical raw materials are used for producing the exemplary embodiments of glasses.

The well homogenized glass batch was melted, refined and homogenized in the laboratory in a Pt crucible at 1420°C . Subsequently the glass was cast and cooled at 20 K/h.

Table 1 shows a summarizes an exemplary melt example of a 0.5 l melt:

Oxides	% by weight		Raw material	Initial weight (g)
SiO ₂	69.98		SiO ₂	772.65
B ₂ O ₃	11.19		H ₃ BO ₃	219.5
Na ₂ O	9.49		NaNO ₃	287.79
K ₂ O	7.29	3.8	K ₂ CO ₃	61.69
		3.49	KNO ₃	82.78
CaO	0.2		CaCO ₃	3.94
BaO	1.35		Ba(NO ₃) ₂	25.38
TiO ₂	0.20		TiO ₂	2.22
Sb ₂ O ₃	0.30		Sb ₂ O ₃	3.31

The properties of the ~~thus-obtained~~ glass of Table 1 are indicated in Table 2, Example 3.

Table 2 shows 9 examples of glasses according to the invention (1 to 9) with their compositions (in % by weight on an oxide basis) and their essential properties:

Example No.

Oxides	1	2	3	4	5	6	7	8	9
B ₂ O ₃	11.21	11.20	11.19	11.18	11.17	11.15	11.12	11.10	11.07
BaO	1.35	1.35	1.35	1.35	1.35	1.34	1.34	1.34	1.34
CaO	0.20	0.20	0.2	0.20	0.20	0.20	0.20	0.20	0.20
K ₂ O	7.31	7.30	7.29	7.28	7.28	7.26	7.25	7.23	7.21
Na ₂ O	9.51	9.50	9.49	9.48	9.47	9.45	9.43	9.41	9.39
Sb ₂ O ₃	0.28	0.30	0.3	0.30	0.30	0.30	0.30	0.30	0.30
SiO ₂	70.13	70.05	69.98	69.91	69.84	69.70	69.56	69.42	69.21
TiO ₂	0.01	0.10	0.20	0.30	0.40	0.60	0.80	1.00	1.30
Properties									
λ_c (d = 2 mm) [nm]	283	295	302	304	308	312	315	318	320
n_d (20 K/h)	1.51423	1.51474	1.51527	1.51566	1.51633	1.51718	1.51805	1.51986	1.52056
v_d (20 K/h)	64.32	64.15	63.90	63.69	63.48	63.01	62.60	62.03	61.58
$\alpha_{(20/300^\circ\text{C})}$ [$10^{-6}/\text{K}$]	8.2	8.2	8.1	8.2	8.2	8.1	8.1	8.1	8.1
Tg[°C]	571	573	570	572	575	568	567	578	578

The absorption edge situation, dependent upon the TiO_2 content, for a given glass composition is plotted in Fig. 1. As shown, the absorption edge ~~situation~~ can be set in a targeted and reproducible manner as a result of the dosed addition of TiO_2 .

German Patent Reference 102 45 880.4-45, the priority document corresponding to this invention, and its teachings are incorporated, by reference, into this specification.